

Technical Data Sheet

Palchem CPE 135A Chlorinated Polyethylene

Typical Physical Properties	
Appearance	Powder
Chlorine Content	35 %
Hardness (Shore A)	60
Heat of Fusion	2.0 J/g
Volatiles	<0.30 %
Antiblock Content	2.0%
Screen Residue (on 0.9 mm)	<2.0%
Bulk Density	0.5 g/ml
Tensile Strength	> 6.0 Mpa
Stability @ 165° C	> 8 minutes
Applications	
Impact Modifier for Pipes	
Profiles	
Wire & Cables	
Food Contact	Not Approved
Packaging	
25 kg bags	
Manufactured in China	
Regulatory Information	
No Special Requirements	