



## Micronized and treated Calcium Carbonate

### Main applications:

Rigid PVC extrusion (profiles, pipes, conduits, venetian blind), injection moulding of PVC fittings, PVC masterbatches, PE and PP masterbatches, rubber blends, injection moulding of PP, BOPP, antiblock and antislip PE bags, silicone sealants.

### Chemical Composition (Before treatment)

CaCO <sub>3</sub>	98.84 %
MgCO <sub>3</sub>	0.87 %
Al <sub>2</sub> O <sub>3</sub>	0.057 %
Fe <sub>2</sub> O <sub>3</sub>	0.011 %
Sn	< 0.001 %
Pb	< 0.001 %
Cd	< 0.0001 %
Mn	0.0074 %
Cu	< 0.0001 %
SiO <sub>2</sub>	0.10 %
Loss of weight on calcination	43.7 %

*Measured by I.C.P.*

### Physical Characteristics

### Method

#### Granulometry

Statistic mean diameter	3.6 µm	Mastersizer S
D 50	2.0 µm	Mastersizer S
45 µm Sieve retention	< 0.1 %	ISO 787R/7

#### Whiteness

#### Dry

#### DOP

Spectraflash SF450

L	97.7	79.0
a	0.0	-0.7
b	1.2	5.0

Moisture	< 0.1%	ISO 787R/2
----------	--------	------------


Oil Absorption	16 g/100 g CaCO <sub>3</sub>	ISO 787R/5
----------------	------------------------------	------------

DOP Absorption	20 g/100 g CaCO <sub>3</sub>	ISO 787R/5
----------------	------------------------------	------------

Specific surface area	3.5 m <sup>2</sup> /g	B.E.T.
-----------------------	-----------------------	--------

Bulk density (untamped)	0.70 Kg/l	ISO 787R/11
-------------------------	-----------	-------------

### GRANULOMETRIC DISTRIBUTION



All data here presented are average values representative of the production and hence they are provided for information purposes only and can not be considered contractual. The product conforms to the requirements of the Food Chemical Codex and the BGA (Germany).

#### Commercial Department

Balmes 49  
E-08007 Barcelona  
Spain  
Tel.: + 34 93 454 53 93  
Fax: + 34 93 323 66 73

#### Headquarters

Ctra. N-340 Km. 1.196  
E-43719 Bellvei (Tarragona)  
Spain  
Tel.: + 34 977 168 103  
Fax: + 34 977 168 112

#### Albox - Almería Plant

Polígono Industrial  
E-04800 Albox (Almería)  
Spain  
Tel.: + 34 950 633 004  
Fax: + 34 950 633 147

#### Reverté GmbH

Weissshausstrasse 26  
D-50939 Cologne  
Germany  
Tel.: + 49 (0) 221 942012 0  
Fax: + 49 (0) 221 413795